

# norament xp trac nTx

Rubber tile floor covering combining a rich, contrasting granular design with a with a grain structure surface. This fast installation system pairs a nora® rubber floor covering with a factory-applied adhesive. The flooring is cleanly and safely installed in a few steps then immediately ready for use.



## **Product Data**

Product: norament® xp trac™ nTx™ resilient tile floor covering, Article 3134

Description: nora® vulcanized rubber compound xp with environmentally compatible color pigments that are free of toxic heavy metals like lead, cadmium, or mercury

Material Size: 39.53" x 39.53" (1004mm x 1004mm)

Thickness: 0.14" (3.5mm)

Dimensional Stability: Meets requirements

Composition: Homogeneous rubber compound with a random scattered design

Colors: 4 standard; additional colors available with minimum order

Surface: Grain structure

## **Technical Data**

|  |  |
|--|--|
| Flammability (E648/NFPA 253):<br>≥ 0.45 watts/sq. cm for Class 1 is required | NBSIR 75 950, 0.68   |
| Smoke Density (ASTM E662/NFPA 258):<br>< 450 is required                     | NBS, 372 (flaming) and 284 (non-flaming)   |
| Surface Burning (CAN/ULC-S102.2):  | FSC1 of 55 and SD of 545   |
| Slip Resistance (ASTM D2047):<br>≥ 0.5 is required                           | Static coefficient of friction, Neolite dry 0.99 Neolite wet 0.98                  |
| Bacteria Resistance (ASTM E2180/ASTM G21):                                   | Resistant to bacteria, fungi, and micro-organism activity                          |
| Sound Absorption (ASTM E2179):   | ΔIIC 15 (compare only Δ values)  |
| Hardness (ASTM D2240):<br>≥ 70 is required                                   | Shore type "A", 89   |
| Static Load (ASTM F970):<br>≤ 0.005 inches with 250 lbs. is required         | Residual compression of 0.005 inches with 800 lbs.                                 |
| Rolling Load Limit (ASTM F2753):   | ≤ 850 lbs. / sq. inch; will accept forklift traffic                                |
| Abrasion Resistance (ASTM D3389):<br>≤ 0.035 oz. (1.0g) is required          | 1.1 lbs. (500g) load on H-18 wheel with 1000 cycles, 0.005 oz. (0.13g) weight loss |
| Oil & Grease Resistance (EN/ISO 26978):                                      | No   |

## **Environmental Attributes**

Carbon: All flooring products 3rd party verified carbon neutral throughout their entire life cycle through the Interface Carbon Neutral Floors™ program. Learn more at [www.interface.com/carbonneutral](http://www.interface.com/carbonneutral).

Indoor Air Quality: GREENGUARD Gold Certified for low VOC emissions in compliance with CDPH 01350

Material Composition: Free of added formaldehyde, heavy metals and ortho-phthalates, fluorinated chemicals (PFAS), and halogenated flame retardants

Production Plant Certifications: ISO 9001:2000, ISO 14001

## **Installation**

Site Conditions: The installation area must be fully enclosed, weather tight, and climate controlled between 63°F and 75°F and 40% to 60% ambient relative humidity (RH) for at least 48 hours prior, during and 72 hours after installation.

Adhesive: Factory-applied

Unique Characteristics:

- Good for very heavy traffic
- Superior footfall sound absorption
- Enhanced slip resistance
- High fire-retardant properties
- Monolithic seamless installation with coordinating weld
- Welding required
- No moisture limit or testing required
- Immediately open to traffic with no down time
- Specially designed to meet applications challenged with recurring wet areas, requiring enhanced slip resistance and ultra-durability

For complete installation instructions refer to the nora nTx Installation Instructions.

## **Care and Cleaning**

No finishes/coatings or harsh chemicals necessary. A post-installation cleaning must be performed before the area is occupied. Refer to the nora Maintenance Guidelines.

## **Wheel Types**

No metal or hard plastic wheels, the shape of the contact surface of wheels must be flat with round edges. The shore hardness must be type A  $\leq$  90.

## **Storage**

nora nTx flooring can be stored within a temperature range of 50°F (10°C) to 80°F (27°C) under the following conditions: Pallets must remain intact with sheet goods standing on end, undamaged, not be stacked, be in a permanently dry environment, and with no direct sunlight. However, all adhesives and cold weld must remain at room temperature without freezing.

## **Warranty**

Limited 10-year bond warranty and 15-year warranty. Refer to the nora nTx and nora Product Warranties - Americas.

Current nora Installation Instructions, Guide Specifications, Maintenance Guidelines, and Product Warranties, can be found at [www.nora.com](http://www.nora.com).

nora®, norament®, and noraplan® are trademarks owned by nora systems GmbH and registered in the United States, Canada, and other countries. All other trademarks are the property of their respective owners.

Updated: October 2022