

# Technical data

noraplan® ultra grip mobil (931), design with granite, surface: reflection-breaking

	Test method	Requirements	Average test results from running production
<b>CE conformity</b>	<b>EN 14041</b>		<b>Manufacturer:</b> nora systems GmbH, D-69469 Weinheim
DoP-No.	EN 14041		0033
Thermal conductivity	EN 10456	$\lambda = 0.17 \text{ W/(m}\cdot\text{K)}$	Fulfilled
Dynamic coefficient of friction	EN 13893	DS	Fulfilled
Reaction to fire	EN 13501-1	Not bonded	B <sub>s</sub> -s1

## Properties acc. to EN 1817

Thickness	EN ISO 24346	Mean value $\pm 0.15 \text{ mm}$ acc. to EN 1817	2.0 mm
Dimensional stability	EN ISO 23999	$\pm 0.4 \%$	$\pm 0.3 \%$
Cigarette-burn resistance	EN 1399	Procedure A (stubbed out) $\geq$ level 4 Procedure B (burning) $\geq$ level 3	Fulfilled
Flexibility	EN ISO 24344, procedure A	Mandrel diameter 20 mm, no fissuring	Fulfilled
Hardness	ISO 48-4	$\geq 75$ Shore A acc. to EN 1817	85 Shore A
Residual indentation	EN ISO 24343	Mean value $\leq 0.15 \text{ mm}$ at thickness $< 2.5 \text{ mm}$	0.05 mm
Abrasion resistance at 5 N load	ISO 4649, procedure A	$\leq 250 \text{ mm}^3$	130 mm <sup>3</sup>
Colour fastness to artificial light	ISO 105-B02, procedure 3, test conditions 6.1 a)	At least level 6 on the blue scale; $\geq$ level 3 on the grey scale	Grey scale $\geq$ level 3 acc. to ISO 105-A02

## Additional technical properties

Weight	EN ISO 23997		$\sim 3.36 \text{ kg/m}^2$
Tear strength	ISO 34-1, method B, procedure A		31 kN/m
Anti-slip properties	DIN 51130	Acc. to BGR 181	R 11
	BS 7976 TRRL Pendulum		36+ Wet & Dry
Improvement in footfall sound absorption	ISO 10140-3		6 dB
Effect of chemicals	EN ISO 26987		Resistant depending on concentration and time of exposure*
Electrical propensity when walked upon	EN 1815		Antistatic, charging $< 2 \text{ kV}$

\* In case of increased impact of oils, grease, acids, alkalis and other aggressive chemicals please contact us.

EN 1817: Specification for homogeneous and heterogeneous smooth elastomer floor coverings

Colour variations due to different production batches as well as technical alterations to improve the product have to be accepted.