

Product Information

noraplan[®] mobil (mix 932)

Designs: stone, stone plus, grip, grip plus, effect, eco, plus, mega, signa and sentica

noraplan[®] mobil (mix 932) are single-layered rubber floor coverings for heavy traffic areas. **noraplan[®] mobil (mix 932)** floor coverings have been especially developed for the use and the special requirements in rail vehicles and are available in sheets and tiles in the above-named designs. The highly resilient and particularly tear-resistant material can be easily processed even in the most difficult installation situations. The floor coverings are fire-resistant and free of polymers containing chlorine.

Technical data Properties acc. to EN 1817	Test method	Requirements	Average test results from running production
Thickness	EN ISO 24346	Mean value \pm 0.15 mm of nominal value	3.0 mm
Dimensional stability	EN ISO 23999	\pm 0.4 %	\pm 0.2 %
Cigarette-burn resistance	EN 1399	Procedure A (stubbed out) \geq level 4 Procedure B (burning) \geq level 3	Fulfilled
Flexibility	EN ISO 24344, procedure A	Mandrel diameter 20 mm, no fissuring	Fulfilled
Hardness	ISO 48-4	\geq 75 Shore A	85 Shore A
Residual indentation	EN ISO 24343	Mean value \leq 0.20 mm	0.07 mm
Abrasion resistance at 5 N load	ISO 4649, procedure A	\leq 250 mm ³	180 mm ³
Colour fastness to artificial light	ISO 105-B02, procedure 3, test conditions 6.1 a)	At least level 6 on the blue scale, \geq level 3 on the grey scale	Grey scale \geq 3 acc. to ISO 105-A02

Additional technical data			
Weight	EN ISO 23997		\sim 4.75 kg/m ²
Slip resistance	DIN 51130		R 9* R 10* (reflection-breaking surf.)
Improvement in footfall sound absorption	ISO 10140-3		10 dB
Effect of chemicals	EN ISO 26987		Resistant depending on concentration and time of exposure ^(A)
Electrostatic behaviour when being walked upon	EN 1815		Antistatic, charging < 2 kV

Fire behaviour / smoke behaviour			
Fire behaviour	EN 13501-1		B _f -s1
	EN 45545	Hazard Level	HL1*
	DIN 5510-2		SF3*
Smoke density / Smoke toxicity	NF F 16-101 (NF X 10-702 / X 70-100)	NF F 16-101 for grid 5 / 8	F1*
Smoke toxicity	ISO 5659-2	DIN 5510-2	FED \leq 1*

Colour variations due to different production batches as well as technical alterations to improve the product have to be accepted.

* Tested and certified by an independent testing institute.

^(A) In case of increased impact of oils, greases, acids, alkalis and other aggressive chemicals please contact us.

Standard measures: Rolls 1.22 m x 12 m

Special measures: Delivery in another thickness, customized dimensions as well as in KITS upon request.

Custom-made designs and colors of **noraplan[®] mobil (mix 932)** with smooth or reflection-breaking surface are subject to minimum order quantities.

Unless agreed otherwise, the sort statement PQC009 is applicable in its current version.

Further product information is available in the current assortment brochure or on www.nora-transportation.com.